

DATOS DE LA MUESTRA

SITIO:	GRAVAS ARGENTINAS - Río Cuarto		
Muestra Nro.:	6-8 mm		

TIPO DE TAMIZADO	EN SECO	Peso muestra	582.4 g
------------------	---------	--------------	---------

Tamiz Nro		3/4	3/8	4	10	20	40	200		
Abertura (mm)	0	0	0	19	9.5	4.75	2	0.85	0.425	0.075
% Pasante	0.0	0.0	0.0	100.0	83.9	1.5	0.05	0.04	0.04	0.0
% Retenido acumulado				0.0	16.1	98.5	99.9	100.0	100.0	100.0
% Retenido parcial				0.0	16.1	82.4	1.4	0.0	0.0	0.0

Pasa tamiz N° 4 (4,75 mm):	1.5 %
Pasa tamiz N° 10 (2.0 mm):	0.1 %
Pasa tamiz N° 40 (0,425 mm):	0.0 %
Pasa tamiz N° 200 (0,075 mm):	0.0 %
D60:	7.77 mm
D30:	6.04 mm
D10 (talla efectiva):	5.10 mm
Coefficiente de uniformidad (Cu):	1.5
Grado de curvatura (Cc):	0.9

Fracciones presentes según SUCS	
% en peso	
Grava gruesa (> 19 mm):	0.0 %
Grava fina (19 - 4.75 mm):	98.5 %
Arena gruesa (4.75 - 2 mm):	1.4 %
Arena media (2 - 0.425 mm):	0.0 %
Arena fina (0.424 - 0.075 mm):	0.0 %
Limo y arcilla (< 0.075 mm):	0.0 %

CLASIFICACIÓN UNIFICADA: GP

